

Thermosetting Acrylics

Products	% NVM (Volatile/ solvent)	Acid Value (mg KOH/ gm)	Color Hazen value APHA	Viscosity Poise/ Gardner Scale@25°C	Description / Uses
TSA 7010XB50	50.0 +/- 2.0 (Xylene/BuOH)	10.0 max	50.0	7.0 - 11.0	Suitable for automotive metallic base coat, clear / pigmented top coats and general stoving enamel.
TSA 7020XB50	50.0 +/- 1.0 (Xylene/BuOH)	10.0 max	50.0	2.1 - 4.2	For general industrial finish, consumer electronics and coil coatings.